





Bluesil™ VICURE #2

October 2017

Cure Accelerator

Description	Bluesil™ VICURE #2 is a Stannous Octoate tin complex. It is a cure accelerator when used in conjunction with a Condensation base and Catalyst combination.
Applications	Cure accelerator for use with Condensation (tin) rubber compounds
Typical Properties	<ul style="list-style-type: none"> • Color Clear Clear, yellowish liquid • Consistency Pourable • Specific Gravity 1.26 • Flash Point, open cup, °C (°F) 121 (250) <p><i>Please note: The typical properties listed in this bulletin are not intended for use in preparing specifications for any particular application of Bluesil™ silicone materials. Please contact our Technical Service Department for assistance in writing specifications.</i></p>
Mix Ratio	Materials accelerated with Bluesil™ VICURE #2 will cure very rapidly. Experimentation is recommended to determine mix ratio and cure rate desired. Twenty (20) drops equals approximately 1 gram. Addition of 0.1%, by weight, will reduce pot life and Demold time by 50%.
Storage and shelf life	Bluesil™ VICURE #2 can be stored up to 730 days. Refer to packaging for more details on storage and shelf life.
Safety	This rubber system uses an organometallic tin catalyst, which may irritate or burn skin and eyes upon contact. If eye contact occurs, flushing with water for at least 15 minutes should relieve discomfort. If irritation or discomfort persists, obtain medical attention. Please consult the Safety Data Sheet of Bluesil™ VICURE #2 .
Packaging	Bluesil™ VICURE #2 is available in 110 gram containers.

Bluesil™ is a registered Trademark of **Elkem SILICONES**

 EUROPE	 NORTH AMERICA	 LATIN AMERICA	 ASIA PACIFIC
<p><i>Elkem Silicones France</i> 21 Avenue Georges Pompidou F69486 Lyon Cedex 03 FRANCE Tel. (33) 4 72 13 19 00 Fax (33) 4 72 13 19 88</p>	<p><i>Elkem Silicones USA</i> Two Tower Center Boulevard Suite 1601 East Brunswick, NJ 08816-1100 United States Tel. (1) 732 227 2060 Fax (1) 732 249 7000</p>	<p><i>Elkem Silicones Brazil Ltda.</i> Av. Maria Coelho Aguiar, 215 Bloco G - 1º Andar 05804-902 - São Paulo - SP - Brazil Tel. (55) 11 3747 7887 Fax (55) 11 3741 7718</p>	<p><i>Elkem Silicones Hong Kong Trading Co. Ltd.</i> Unit C, 18/F Manulife Tower 169 Electric Road North Point-Hong Kong Tel. (852) 3106 8200 Fax (852) 2979 0241</p>
<p>Warning to the users The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. Elkem SILICONES guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document and Elkem SILICONES is at their disposal to supply any additional information.</p>			